**Designing advanced biochar products for maximizing greenhouse gas mitigation
potential**

Sanchita Mandal^{1*}, Binoy Sarkar¹, Nanthi Bolan^{2,3}, Jeff Novak⁴, Yong Sik Ok⁵, Lukas Van
Zwieten⁶, Bhupinder Pal Singh⁷, M.B. Kirkham⁸, Girish Choppala⁹, Kurt Spokas¹⁰ and Ravi
Naidu^{2,3}

¹ Future Industries Institute, University of South Australia, Mawson Lakes, SA 5095,
Australia

² Global Center for Environmental Remediation, University of Newcastle, Callaghan, NSW
2308, Australia

³ Cooperative Research Centre for Contamination Assessment and Remediation of the
Environment, P.O. Box 486, Salisbury, SA 5106, Australia

⁴ Coastal Plains, Soil, Water, and Plant Research Center, US Department of Agriculture,
Agricultural Research Service, 2611 West Lucas Street, Florence, SC 29501, USA

⁵ Korea Biochar Research Center and Department of Biological Environment, Kangwon
National University, Chuncheon 200-701, Republic of Korea

⁶ NSW Department of Primary Industries, 1243 Bruxner Highway, Wollongbar, NSW 2477,
Australia

⁷ NSW Department of Primary Industries, Elizabeth Macarthur Agricultural Institute,
Woodbridge Rd, Menangle, NSW 2568, Australia

⁸ Department of Agronomy, Kansas State University, Manhattan, KS 66506-5501 USA

⁹ Southern Cross GeoScience, Southern Cross University, Lismore, NSW 2480, Australia

¹⁰ USDA-ARS, 1991 Upper Buford Circle - 439 Borlaug Hall, St. Paul, MN 55108, USA

Corresponding author:

Ms Sanchita Mandal; University of South Australia

e-mail: sanchita.mandal@mymail.unisa.edu.au; Tel: +61 8 83026254

Abstract

Greenhouse gas (GHG) emissions from agricultural operations continue to increase. Carbon (C) enriched char materials like biochar have been described as a mitigation strategy. Utilization of biochar material as a soil amendment has been demonstrated to provide potentially greater soil GHG suppression due to its interactions in the soil system. However, these effects are variable and the duration of the impact remains uncertain. Various (nano) materials can be used to modify chars to obtain surface functionality to mitigate GHG emissions. This review critically focusses on the innovative methodologies for improving char efficiency underpinning GHG mitigation and C sequestration.

Keywords

Activation, Charcoal, Carbon dioxide, Grafting, Soil health, Nitrous oxide, Plant nutrients

1. Introduction

Rising emission of greenhouse gases (GHG) from agricultural lands, due to anthropogenic activities of burning fossil fuels and land-use changes (deforestation) are major contributors to global warming [1]. Agricultural activities collectively contribute between 5 to 6 petagrams carbon dioxide (CO₂) equivalents (approximately 10 to 12%) of the total global GHG emissions [2]. This is primarily due to nitrous oxide (N₂O) emissions from mineral and organic fertilizers applied in soils. Additionally, burning of fossil fuels and deforestation have resulted in an increase of global surface temperature up to 0.8 °C during the 20th century, which likely will increase to 1.4 °C–5.8 °C in the 21st century [3, 4]. This increase in global temperature is attributed to the greenhouse effect caused by CO₂ as the major source of GHG. However, the global warming potential (GWP) of N₂O is 298 times greater than CO₂ [4, 5], so the former can trap more heat in the atmosphere compared to the latter. Among all the sectors that are responsible for GHG production, agriculture contributes a significantly large share [3].

Application of organic amendments in agricultural soils can alter GHG emissions, while improving soil physical, chemical, and biological properties [6]. To mitigate GHG emission, carbonized biomass such as biochar, graphite, charcoal and activated carbon (AC) can be used [7, 8]. Biochar materials are solid residuals from pyrolysis processes, and can contain up to and indeed beyond 80% C, representing around 30-50% of the original biomass C. They can lower GHG emissions, both directly and indirectly. These direct and indirect effects and their outcomes are summarized in Figure 1. The nomenclature of char materials has not been standardized fully across all scientific fields. They can be produced during combustion, gasification and pyrolysis of any C containing material, like burning of biomass, incomplete combustion of fossil fuel (black carbon; soot), and production of hydrocarbons (carbon black; soot) [9, 10]. Since the mid-1990s char materials attracted enormous attention because of

their various beneficial applications [11]. Char materials can (a) potentially sequester C in soil [12-14], (b) reduce nitrogen (N) loss from soil in terms of N₂O emission [15] and ammonia (NH₃) volatilization [16, 17], (c) improve nutrient retention capacity of soils and reduce runoff and leaching losses [18-21], (d) improve plant growth [9], (e) remediate contaminated soil and water [22-25], and (f) improve soil health [11, 18] by supplying nutrients to the roots and microbes directly from the source, or indirectly by their ability to sorb and retain nutrients [26, 27]. Chars have also been shown to increase N-use efficiency both in a short glasshouse study [28] and field scale studies [29]. The sorbed nutrients gradually release from char and become slowly available to plant roots and microorganisms. A meta-analysis of impacts of biochar on soil emissions of N₂O has shown that on average, a 54% lowering of emissions may be achieved [15]. It was shown that woody and herbaceous feedstock had a greater impact on lowering of emissions than biochars derived from manure or biosolid. Shafeeyan, Daud [13] reported that soil treated with AC (plum shell based granular AC) adsorbed more CO₂ than untreated soil. Aguilar-Chávez, Díaz-Rojas [14] also found that charcoal with an application rate of 4.5% could increase soil CO₂ sorption by more than 37%. Biochars have been shown to increase soil C density in the field both through the increased C added via biochar, and also through new plant C allocation [29]. Char materials are emerging as a low-cost sorbent for reducing risks of inorganic pollutants (lead, copper, arsenic, aluminum and chromium) in soils [30-32], and lowering the concentration or bioavailability of organic pollutants arising from various agricultural, industrial and farming activities [33, 34]

[Figure 1]

Salient characteristics of char materials for GHG reduction include surface area, functional groups, pore size, pore space, elemental composition, pH, and sorption sites. The presence of functional groups such as the carboxylic or hydroxyl groups on biochar surfaces can adsorb

GHG and react with them (e.g., N₂O) thus reducing their emissions when compared to unamended soil [35]. To further improve the efficacy of char materials in lowering GHG emissions, they can be modified to obtain specific chemical characteristics, elemental composition and structural features [36]. Char materials can also be a suitable support/host matrix for incorporating highly reactive nanoparticles, which can enhance the mitigation of GHG emissions [37]. However, more research is required to identify the characteristics of chars that can be improved by combining other materials. Therefore, this paper aims to review the existing and potential innovative methodologies for improving char efficiency underpinning GHG mitigation and C sequestration in the context of a system where improved plant productivity is sought.

2. Greenhouse gasses and the environment

Increased GHG emission is a serious threat to our environment [38]. Due to anthropogenic activities, the temperature has increased by 0.6 °C–0.8 °C globally between 1951–2010 [3]. Emissions of GHG and changes in land use patterns including agriculture and urbanization are the most important elements which impact the climate [39]. Wastewater treatment plants and livestock are also important sources of GHG emission and onsite aerobic biological wastewater treatment is the highest contributor in an urban setting [40, 41]. Carbon dioxide contributes the highest proportion to the greenhouse effect because of its high concentration in the atmosphere [4]. Concentrations of the greenhouse gasses, e.g., CO₂, CH₄, and N₂O, due to anthropogenic activities are increasing at a rate of 0.4, 0.6 and 0.25% per year, respectively [42].

Because of different atmospheric half-lives and radiative forcing of the GHGs, they are assigned a different GWPs [43]. Trace gases including CH₄ and N₂O absorb nearly 300 and 25 times more infrared radiation, respectively, than CO₂, and contribute 15 and 5-6% anthropogenic greenhouse effect [44].

Among various sectors, agriculture contributes 20% of total GHG emissions (N_2O , CO_2 , and CH_4) [45]. Land conversion from forests and pastures to croplands accounts for about 12-20% of the GHG emissions [46]. Waste management activities also contribute to the emissions (4%), while disposal of waste in landfills generates CH_4 . Livestock are responsible for about 12% anthropogenic GHG emission [47, 48].

Climate change can have an adverse impact on agricultural production and environmental quality. For example, as estimated by statistical models, the wheat yield in India dropped by 36% in 2010 as compared to 1980, because of climate change and emissions of other pollutants [49]. The increasing concentrations of atmospheric GHGs have catalyzed the chances of drought and flood in different regions in India [49]. An overall reduction in the quality of available water runoff was also noted [50]. Furthermore, the increasing CO_2 levels affected soil microbial activity and water content. Furthermore, van Groenigen, Osenberg [51] found that increases in CO_2 level triggered N_2O emission from upland soils and CH_4 emission from paddy soils and natural wetlands.

Investments into field improvements of agriculture have avoided up to 161 gigatons of CO_2 emissions since 1961 [49]. Changing the food habits, for example, shifting from red meat and dairy products to chicken, fish, and vegetables based diets could potentially decrease the GHG emissions [52]. Also, changes in agricultural practices such as growing lignocellulosic energy crops, e.g., willow (*Salix* spp.) and elephant grass (*Miscanthus x giganteus*), which give much higher yield, would lower GHG emission in comparison to arable crops [53]. Adapting less intensive tillage operation is also a well-known strategy to tackle CO_2 emission from soils [54, 55].

3. Nitrogen dynamics and carbon cycle

3.1. Nitrogen dynamics and gaseous N emissions

It was reported that an average 4-6 teragram (Tg) of N₂O-N is being released into the atmosphere annually through agricultural activities, mainly from the use of mineral and organic N fertilizers [56]. An emerging pool of information shows that biochar, or indeed, a biochar system, is able to provide opportunities for mitigation of N₂O emissions through altered N and C cycling [59]. Nitrogen is an important nutrient for plant growth, development, and reproduction. Most plants access N from soil, either through uptake of mineral N, or through biological N₂ fixation. When N is added to the soil, it undergoes various transformation processes and can produce gaseous products including ammonia (NH₃), N₂O and N₂ (Figure 2). The loss of N through gaseous emissions decreases the amount of soil available N to plants and contributes to GHG inventories.

[Figure 2]

3.2. The carbon cycle and CO₂ emissions

Carbon is an important macro element for plant development, and plants usually take up C as CO₂ from air during photosynthesis [57]. Carbon circulates in an endless process between the earth's surface, oceans, plants and soils (Figure 3). Through this process C is converted into CO₂ as a natural component of the atmosphere that protects the earth's surface from radiation by reflecting it back into the atmosphere. This phenomenon causes some heat to be generated, which can result in rising temperatures. For this reason CO₂ is called a GHG [58]. When the production of CO₂ exceeds the buffer capacity of the earth's ecosystem, it can result in global warming, i.e., the earth retains heat.

Utilization of biofuel C (e.g., that from maize or sugar cane) instead of fossil fuel can reduce CO₂ emissions, because biofuel C is mainly derived from the atmosphere via current

photosynthesis (fossil fuels result from photosynthesis millions of years ago) [59]. Production of CO₂ due to various anthropogenic activities (industry and agricultural activities) have increased its concentration from 284 ppm in 1832 to 397 ppm in 2013 [60]. As noted, a large amount of CO₂ is produced from the agricultural sector. Schimel [61] reported that the agriculture sector contributes about 20% of total anthropogenic CO₂ emission. Anthropogenic CO₂ comes from several sources including biomass burning, tillage practice, accelerated soil organic matter (SOM) mineralization, and microbial decay [4]. Soil is a large global C sink being around 2500 gigatons (Gt C), including about 1550 Gt of soil organic carbon and 950 Gt of soil inorganic carbon [62].

[Figure 3]

4. Properties of biochar which alter N cycling, N₂O, and CO₂ emissions

Meta-analysis of the impacts of biochar on N₂O emissions have shown that the properties of biochar are critical in controlling emissions. For example, Cayuela, Van Zwieten [15] showed that biochars derived from crop and woody residues resulted in over a 50% decrease in emissions, while biochars from other feedstock might not provide, on average, any meaningful opportunities for lowering emissions. The quantity of biochar applied to soil has been shown to be important, with mitigation opportunities only becoming evident when biochar was amended at or above 2% w/w into soil [15]. Slight mitigation opportunities were detected in a meta-analysis by Cayuela, Van Zwieten [15] when biochar was amended at 1-2% w/w to the soil. Interestingly, biochar amendments were effective at lowering emissions in alkaline, neutral and slightly acid soils, but when pH was below 5.5, no effect was detected [15]. This may present opportunities for modification of biochars, or indeed selection of biochars that can modify soil pH to lower N₂O emissions. Most recently, Cayuela, Jeffery [63] updated the previous meta-analysis [15] with new data, and they showed that an important factor in the mitigation of N₂O was the molar H/C ratio of the biochar. Biochars

with a molar $H:C_{org}$ ratio of <0.3 , indicative of a high degree of aromatic condensation, lowered N_2O emissions by 73%, while biochars with a molar $H:C_{org}$ ratio of >0.5 were less effective, lowering N_2O emissions by 40%. This was not a surprising result in light of previous information showing that woody biomass and crop residue biochars (which tend to have lower molar H/C ratios) were more effective than manure-based biochars. Clearly, there are both physicochemical and biological controlling factors in the mitigation of N_2O .

Denitrification, a biologically “broad process” [64], requires both a labile C and N supply to function in soil, therefore biochars that limit the bioavailability of either of these substrates may be expected to lower emissions of N_2O . Evidence exists that biochar can limit the supply of mineral N [35, 65], thus lowering the substrate needed by denitrifiers. Similarly, biochars were shown to induce negative priming effect [66, 67] and to sorb labile C in soil. For example, Sarmah, Srinivasan [68] showed that biochars with higher production temperatures and associated surface areas exhibited a greater sorption capacity of hormones when amended into dairy farm soils. Similarly, Martin, Kookana [33] showed that biochar amended soils sorbed a greater amount of herbicides. Optimizing the sorptive capacity of biochars presents opportunities to restrict C and N substrates required by denitrifiers, and therefore provides an opportunity to lower the emission of N_2O . However, the longevity of these traits in soil remains unknown. Biochar addition to soil can change soil properties that influence denitrification. For example, biochars were shown to ameliorate soil compaction and bulk density [69] which would affect denitrification. A wood based biochar at 5% w/w increased porosity (measured by X-ray computed tomography or μCT) in a Vertisol from 7.5 to 13.4% [70]. Importantly, increases in pore connectivity were observed across two clay-dominated soils (Vertisol and Ferralsol) and a sand-dominated soil (Arenosol) over 15-month incubation. Soil with 1% biochar had an increase in the rate of drainage in the Vertisol and a 20% increase in the available water content of an Arenosol [70]. These changes in the soil

physical characteristics suggested that biochar might allow faster drainage in clay soils and allow an improved air flow into the soil profile, and therefore reduce waterlogging conditions that are conducive to denitrification. This requires further exploration and testing at both the laboratory and field scales.

Some biochars were shown to carry organic compounds that could impact microbial toxicity in soil. For example, they might contain polycyclic aromatic hydrocarbons (PAHs), polychlorinated compounds, dibenzodioxins and furans, which would form during pyrolysis of the feedstock [71, 72]. PAHs were found to modify the nitrification processes and denitrifying bacterial communities in soil [73, 74]. Spokas [75] investigated the direct impact of biochar-released ethylene on N₂O production from the soil. The result supported the possibility of introducing compounds that modify N cycling, nitrification and denitrification reactions in the soil. For example, 3, 4-dimethylpyrazole phosphate (DMPP) is a nitrification inhibitor that has been studied extensively with the aim of improving N-use efficiency and lowering N₂O production from the soil. Opportunities exist to use biochar as a carrier for this nitrification inhibitor. However; biochar produced from eucalyptus wood with a large surface area (426.4 m² g⁻¹) reduced the inhibitory effect of another nitrification inhibitor dicyandiamide (DCD) in a neutral Cambisol [76]. This work demonstrated that sorptive biochars were more efficient at reducing the efficacy of the nitrification inhibitor than less sorptive ones.

Biochars' influence on the soil microbial communities that are involved in N cycling was reported [65], however, the authors suggested that changes in environmental conditions resulting in N₂O formation were more important than the changes in size or activity of soil microbial communities. Of particular interest are the redox or electron shuttling properties of biochar [77]. Iron (Fe) is an important element in N transformation in soil. Li, Yu [78] showed that reduction and oxidation of N compounds were enhanced when Fe and organic

matter were also oxidized or reduced. Reactions between Fe^{2+} and either NO_3^- or nitrite (NO_2^-) to produce N_2 (reduced species) were energetically favorable. These results suggested that Fe content of biochars should be enhanced before application to soil, or indeed, feedstock such as biosolids should be used [79] which would result in an increase of the Fe content. In the study by Van Zwieten, Kimber [79] lower emissions of N_2O from a Ferrosol were detected with a high Fe-biochar compared to other biochars produced from sludge and wood chips.

Pyrolysed biomass has created research interest as it has been shown to lower greenhouse gas emissions and increase soil C content. Carbon sequestration is one of the key benefits of using char materials as a soil amendment. It has been estimated that chars produced from natural wildfires may represent 15-20% of total C in temperate and coniferous forest soils [80]. In one study, Spokas, Koskinen [81] found that biochar application reduced soil CO_2 emissions. Another study by Case, McNamara [82] also reported that biochar addition at 49 t ha^{-1} in a field trial can suppress soil CO_2 emission up to 53%. The reason of lowering CO_2 emission following biochar amendment may be due to a negative priming effect (outlined in section 6) whereby new C (e.g. Root exudates etc.) in soil are established and not available for microbial degradation. However, other studies have observed that biochar addition in soil has little or no effect on CO_2 ; for example's Wu, Jia [83] found that biochar addition at 0.67, 1.68% rate did not affect soil CO_2 emissions but lowered N_2O emissions significantly.

This section has demonstrated pathways in which biochars may alter N cycling and hence emissions of N_2O (Figure 4). Modifications of biochars to optimize soil pH, soil physical characteristics, redox active elements and to reduce toxic components provide opportunities to mitigate N_2O and CO_2 emissions. It will be critical, however, to first understand the key processes of formation of modified biochars for each soil/climate/agroecosystem, before biochars can be designed to lower emissions of N_2O and CO_2 .

[Figure 4]

5. Char materials for greenhouse gas mitigation

Char materials may be used to mitigate climate change resulting from agricultural GHG emissions [9, 12]. The degradation rate of char materials is slow and these properties may be exploited in the development of slow release fertilizers [84]. Chars are generally produced as a by-product during biofuel processing or during the pyrolysis of organic residues from various biomasses, woods and hydrocarbons to make bioenergy [85]. The properties of char materials can vary depending on varieties of feedstock materials used for their preparation and pyrolysis (or burning) conditions [11, 28, 35, 86, 87]. Table 1 shows specific production methods and characteristics of various char materials.

[Table 1]

5.1. Biochar

Biochar has multi-purpose properties that make it a unique amendment to improve soil health, and it also can remediate environmental contaminants [22, 23]. Biochar is used for mitigating GHG emissions due to its relative stability, ability to act as a long-term nutrient sink in the soil and higher nutrient retention capacity than other organic amendments [9, 86]. It has a range of surface functional groups that can adsorb heavy metals from soil and aquatic environments [32, 86, 88-90]. It can also reduce GHG emissions, such as N_2O , by adsorbing and retaining N in the soil. Woolf, Amonette [91] reported that the annual net emissions of GHG (CO_2 , N_2O , and CH_4) were reduced up to 12% by adding biochar in the soil. In support of this estimate, many researchers have reported the successful application of biochar as a soil amendment for C sequestration [12, 92-94]. Biochar can also provide direct agronomic benefits to plants by supplying nutrients [N, phosphorus (P), potassium (K) and sulfur (S)], and provide indirect benefits through the sorption of elements to retain essential nutrients [26,

27, 88, 95]. Table 2 shows a compilation of some recent reports on the effect of different types of biochars on GHG emissions and soil health.

[Table 2]

Biochar can induce microbial immobilization of nutrients such as N, P, and S in soil, thereby reducing loss of these nutrients through leaching and gaseous emission (e.g., N). Overall, biochar not only improves the agricultural productivity but also sequesters C in the soil, and thus protects the global environment by reducing GHG emissions as well as nutrient leaching from the soil [96].

5.2. Charcoal

Charcoal is generally used as a fuel source and it is produced from wood [97]. Charcoal is a much better fuel than wood because of its lower transport and handling cost compared to firewood [98]. Charcoal has been used for domestic purposes for manufacturing of various industrial chemicals like carbon tetrachloride, sodium cyanide, and carbon disulfide [99], and as a reductant in steel manufacturing. During thermal degradation and carbonisation, the volatile components are removed from the biomass. Charcoal has 85-90% fixed C that can provide a major C sink in the soil [100]. It has specific properties that can help improve soil health (e.g., appropriate pH and water holding capacity) and reduce the rate of N mineralization [101]. Zimmerman [102] reported that charcoal is resistant to microbial degradation, and hence can store C in the soil for long periods of time.

The reduction of CO₂, N₂O, and CH₄ emissions by adding charcoals to the soil is not always uniform (Table 2). The addition can show no effect or even negative effects on the reduction of GHG emissions depending on feedstock types and soil properties [97, 103].

5.3. Activated carbon

Activated carbon is an important material because of its widespread use as an adsorbent, catalytic and catalyst support [104, 105]. This material can be modified in various ways to increase its surface characteristics and thus to enhance mitigation of GHG emissions as well as adsorption of heavy metals in soil. Activated carbon is an important adsorbent especially due to its high micro- and meso-porosity, surface acidic groups, and apparent surface area that increase its activity to adsorb heavy metals like Cd, Pb, and Cu [105, 106]. Two different methods can be used to prepare AC: physical and chemical activation. The physical activation method involves carbonization of raw materials and subsequent activation at high temperature in a CO₂ or steam environment. Steam activation flushes away the oil residues and it opens up the planar sheets. Steam activation method could increase the surface area, micro-porosity and mesopore volume of the products [107]. Chemical activation involves carbonization of previously activated raw materials by potassium hydroxide (KOH) and phosphoric acid (H₃PO₄) [107]. Adsorption of CO₂ requires solid sorbents with a high CO₂ selectivity and capacity. Activated carbon can capture CO₂ by solid adsorption because of its highly porous structure [108]. The adsorption capacity of AC is based on the short-term physical adsorption and it can be improved by introducing NH₃ on its surface for reducing CO₂ emission [108, 109] (Table 3). Ammonia decomposes at high temperatures and produces some radicals (NH₂[•], NH[•], H[•]) and these radicals react with the C surface to form reactive functional groups (-NH₂-, -CN, pyridinic, pyrrolic and quaternary N) [108].

[Table 3]

6. Priming effect of char materials on soil carbon and nutrient cycling

The priming effect (PE) refers to stimulation or stabilization of native soil C through the application of nutrients or organic residues [110]. The PE can be both positive or negative and may occur simultaneously in soil [111]. A positive PE means a net increase in the release

of C and nutrients from native SOM caused by added substrates, and the opposite effect (i.e., immobilization of C and nutrients) for a negative PE [111, 112]. Both positive and negative PE can be caused by direct or indirect alterations of biotic and abiotic processes in the soil. Because char materials contain C and other nutrients such as N and P, they can cause a PE on C and these nutrients in the soil. Most of the times the PE refers only to C and nutrients that undergo microbial transformation (e.g., N, P, and S) [110, 113]. Figure 5 presents an overview of intrinsic char properties and external factors (that char interacts with) and mechanisms leading to either a positive or negative PE in soil.

Certain char properties such as labile C content, surface area, porosity, pH, CEC, C-to-available nutrient ratios, and volatile organics can directly impact priming of native SOM [67, 97, 114, 115]. These properties can be altered by the condition of char production (e.g., pyrolysis temperature, slow or fast pyrolysis), feedstock type (e.g., C-rich and nutrient poor vs. C poor and nutrient rich biomass), or external modifications of char surfaces, pore spaces, or chemistry. The external modifications of char can result from natural ageing, clay addition, chemical oxidation, steam activation, or impregnation during or post-pyrolysis of feedstock biomass [87]. Char in soil could interact with soil C content, texture, clay mineralogy, pH, temperature, and root C input to alter the magnitude and direction of PE, which may vary with char type, char ageing, and soil type [115, 116]. A recent meta-analysis by Maestrini, Nannipieri [117] showed that labile C components in char would induce positive priming (increase native SOM decomposition by 15%) by triggering the microbial activity within a few days to weeks, while physicochemical protective mechanisms may induce negative priming over a longer term. A range of mechanisms have been proposed in a recent review [112] for the PE of char involving changes in biotic processes (e.g., acceleration of microbial metabolism, enzyme production and activity, shifts in microbial community) or abiotic processes (e.g., sorption or immobilization of native substrates, microbial enzymes, biochar-

clay interactions) (Figure 5). The char products and their properties could be modified during or after pyrolysis with the aim to either enhance (i) nutrient release and availability over a short-to-medium timescale to support soil fertility and plant growth *via* positive priming, or (ii) native SOM (C and nutrients) storage to support long-term soil productivity and combat climate change *via* negative priming. However, nutrients would become less available to plants if certain properties such as char's sorption ability are enhanced, e.g., by pyrolysis at high temperatures or *via* physical (steam) or chemical activation without altering certain properties or introducing substrates that enhance labile C components to promote positive priming. It is important to alter char properties in such a way that the modified products enhance both positive and negative PE. However, limited research has been conducted to understand the PE of modified chars on native or freshly added SOM.

[Figure 5]

7. Modification of biochar surface properties

Global interest in using biochar soil amendments has risen predominantly to improve soil fertility [27] and crop productivity [118, 119] as well as to increase C sequestration [12]. Biochar can boost soil fertility levels by the release of nutrients [120] and through improved nutrient retention via the reactive functional groups [121, 122]. Char materials are rich in C content and stable in form so that they can create a long term C or another nutrient sink in the soil [123]. As noted, biochar addition could improve soil quality as well as reduce GHG emissions [12, 85, 124]. The addition of biochar materials in soils could also act as an ideal immobilizer of various contaminants such as antibiotics.

Biochars are increasingly being recognized as multi-functional materials. As such, the chemical characteristics of biochar surfaces are now more closely scrutinized to maximize their role in abiotic and biotic reactions [125]. For example, biochars are known to impact reactions involving nutrient cycling, metal chelation and stabilization, and redox reactions,

which are known to be important for altering plant and microbial responses [125]. Because of these interactions, there is considerable interest in applying biochar technology into new areas including environmental and energy sectors [91].

Recently, the concept of designing biochars for specific application purpose has been proposed [37]. Creating designer biochars is reported to be a more effective approach than simply applying biochar indiscriminately [126]. Scientists have advanced the designer biochar concept by modifying the biochar surface using physical, chemical, and nano-sized materials (Table 4). The purpose of this strategy is to improve the physicochemical and sorptive characteristics of biochars for novel uses such as heavy metal binding [23, 89], organic pollutant sorption [127], and water purification [128].

[Table 4]

7.1. Modification processes

Biochars can be modified using several processes (Table 5). The selection of an individual modification method depends on feedstock type and the target problem (i.e., soil fertility, metal immobilization, etc.). Available feedstock for biochar production includes wood, coconut shells, peat, [129], grasses, nut shells, [130], animal manures [131], etc. The feedstock can be treated either pre- or post-pyrolysis to gain desirable properties. For example, biochars can be treated to have a higher capacity for specific interactions with organic and inorganic chemicals because they have a high surface area, high degree of physicochemical attraction between the adsorbate and C surface, and the appropriate pore size distribution. As shown in Table 5, during the physical processes of biochar treatment, gases (CO₂), air [132, 133] and steam [134] were introduced during the carbonization phase of pyrolysis (700 °C). Higher activation temperatures (700 to 900 °C) were needed to further attenuate the material to increase the surface area and O-containing functional groups [135].

[Table 5]

7.1.1. Impregnation

Impregnation is a process where guest elements (usually metals) are incorporated into the char surface through prolonged wet contact [136]. Following impregnation, char materials are likely to impact GHG emission through electrostatic interaction between the impregnated metal cations and negatively charged C containing functional groups in the SOM (e.g., carboxylic group and lactonic group) [137, 138]. Char modification by impregnation is likely to make them more active in terms of retaining heavy metals from aqueous solution [139, 140]. For example, Wang, Sheng [141] reported that manganese (Mn) impregnated biochar increased the removal efficiency of Pb from 6.4 to 98.9%. Agrafioti [138] also found that Ca^{2+} modified biochar demonstrated a high As removal capacity (>95%). Zhang, Gao [34] prepared iron impregnated biochar with ferric oxide (Fe_2O_3) and found that the modified biochar had a strong sorption of As in aqueous solutions. Nitric acid (HNO_3) is frequently used to remove intrinsic ash and tar of biochar before impregnation. Impregnation of biochar as a catalyst has been reviewed recently by Qian, Kumar [142]. The following reaction scheme shows (Figure 6) how Fe modified biochar can reduce N_2O emission.

[Figure 6]

7.1.2. Oxidation

Oxidation is another modification process where liquid or gaseous compounds (e.g., inorganic acids) are used to modify and purify chars [132, 143]. Two types of oxidation, liquid phase oxidation and gas phase oxidation are generally used. In the liquid phase oxidation process, strong acids like HNO_3 [143], a mixture of HNO_3 and sulfuric acid (H_2SO_4) [144], strong oxidants like potassium permanganate (KMnO_4) in acid solution, or other chemical mixtures, such as hydrogen peroxide/ sulfuric acid ($\text{H}_2\text{O}_2/\text{H}_2\text{SO}_4$) and

hypochlorite solution (HClO_4) [145, 146] have been used to modify, or purify chars. Gaseous phase oxidation includes the use of CO_2 and O_2 gas for modifications [132, 133]. The use of KOH is also known to increase the porosity and surface area of the biochar [142]. For example, Zhang, Gao [34] developed KOH-activated biochar with a surface area of up to $3,500 \text{ m}^2/\text{g}$ with a large pore volume ($1.3\text{-}1.94 \text{ cm}^3/\text{g}$).

Oxidation can modify chars in two different ways: firstly, by opening the pores in char products and subsequent filling with metals, and secondly, by the addition of new functional groups on the surface of chars. Chemical activation which utilizes acids [phosphoric acid (H_3PO_4), HNO_3 , and H_2SO_4] and bases [KOH, sodium hydroxide (NaOH)], is used to modify biochars because they have both dehydration and oxidation characteristics. The feedstock is usually mixed or soaked in a solution of these chemicals before pyrolysis and activation (Table 4). The use of typical acids and bases modifies the biochar by introducing O-containing functional groups into the C matrices [143-145]. Strong oxidizers such as KMnO_4 and HClO_4 also can be used to modify or purify biochars [145, 146]. The degree of modification is also temperature dependent because at higher activation temperatures more O_2 is added to the rings.

Chemical phase oxidation through impregnation of biochars can be completed using metals [e.g., Magnesium (Mg), iron (Fe), aluminium (Al)] that are incorporated into the structural makeup of the biochars [136]. This process also improved the compatibility of chars with other materials such as nanomaterials [145-147]. Following impregnation, biochars can enter into abiotic and biotic reactions that impact nutrient availability [125], GHG production [137, 138], and metal binding [139, 140].

7.1.3. Grafting

The last form of activation is grafting (Table 4). The basic premise of this method is that the surface properties of carbon nanotubes can be modified by the grafting of organic molecules onto them. The technique involves the immobilization of an initiator (Table 4; poly-styrene- N_3) onto the tubes followed by surface-initiated polymerization of an organic compound (sec-butyl L-Li) to form a dense polymer material [148]. In this way, the tubes were made more structurally dense and could enter into secondary reactions such as binding of pollutants [149]. Grafting involved the fusion of guest molecules/elements onto the chars surface functional groups, using the condensation reaction [150]. Grafting through chemical functionalization has resulted in an outstanding compatibility between nano-materials and chars. However, information concerning the grafting of complex polymers on the surface of char materials in order to improve their ability to remediate contaminated environments is scant [151]. Grafting can be done with or without pre-oxidation. There is a range of compounds/materials that can be used to graft a char material, e.g., chitosan (natural biopolymer), polyallylamine hydrocarbon, and various nanocrystals [cadmium selenide- zinc sulfide (CdSe-ZnS) in chloroform ($CHCl_3$), zinc oxide (ZnO) in ethanol and Fe_2O_3 in aqueous solution] [147, 148, 152]. Grafted char shows a wide range of potential application such as use in biomaterials, bioengineering and emerging biotechnology.

7.2. Materials for char modification

A range of compounds/materials can be used to modify chars (Figure 7). However, selection of materials depends on the specific char characteristics that may need to be changed. Various types of materials that can be used to modify chars are listed below:

- Chitosan, a copolymer of 2-acetamido-2-deoxy- β -D-glucopyranose and 2-amino-2-deoxy- β -D-glucopyranose through a β -(1 $\rightarrow$ 4) linkage, is a naturally abundant polysaccharide and generally, it can be obtained by extensive deacetylation of chitin

[147]. Chitosan can be used as an organic glue to attach other materials on char surfaces [32].

- Zero-valent iron (ZVI) can be used to modify char. ZVI particles are inexpensive reducing agents and thus can be used to remediate various contaminants [32, 151, 153]. An additional benefit is that the modified chars could be collected from solution by magnetic separation [154].
- Peroxide (H_2O_2) could be used to modify chars. It was observed that application of H_2O_2 can increase the O-containing surface functional groups like the carboxylic group that can improve heavy metal sorption capacity [155].
- Some nanocrystals such as ZnO, CdSe-ZnS, ferrous oxide (FeO), calcium oxide (CaO), and ferric chloride ($\text{FeCl}_3 \cdot 6\text{H}_2\text{O}$) can be used to modify chars to improve their physical, chemical, and biological properties [147, 148, 152].

[Figure 7]

8. Summary and future research need

This review presents multiple opportunities to optimize the efficacy of biochars for a range of purposes including mitigation of N_2O , stabilization of C in the soil and for reducing the toxicity of heavy metals in soil. Future research is required concerning the following topics:

- Production of chars from sewage sludge and waste materials that can be used to conserve nutrients in the soil and increase soil fertility.
- The introduction of cost-effective modification methods that can lower GHG emissions.
- The performance of field experiments with appropriate controls to get more realistic information.
- Modification of biochar properties using the methods impregnation, grafting, and oxidation to optimize outcomes for lowering GHG emissions. In particular, reactive

surfaces need to be studied in detail because they are critical for capturing and adsorbing GHGs and in improving the pore structure. These parameters are also important in developing slow release fertilizers and increasing water retention in soil. Nanomaterials may also increase the reactivity of char surfaces which may result in improved mitigation of soil GHGs.

Acknowledgement

Sanchita Mandal is thankful to the Department of Education and Training, Government of Australia, for awarding her an Australian Postgraduate Award (APA).

References

1. Xiong, Z., et al., *Influence of NH₃/CO₂ Modification on the Characteristic of Biochar and the CO₂ Capture*. Bioenergy Research, 2013. **6**(4): p. 1147-1153.
2. Smith, E., et al., *Comparison of three simple field methods for ammonia volatilization from manure*. Canadian Journal of Soil Science, 2007. **87**(4): p. 469-477.
3. IPCC, *Climate Change 2013: the physical science basis: contribution of Working Group I to the Fifth Assessment Report of the Intergovernmental Panel on Climate Change*, Cambridge Univ Pr. 2013.
4. Dhillon, R.S. and G. von Wuehlich, *Mitigation of global warming through renewable biomass*. Biomass and Bioenergy, 2013. **48**: p. 75-89.
5. Suddick, E.C. and J. Six, *An estimation of annual nitrous oxide emissions and soil quality following the amendment of high temperature walnut shell biochar and compost to a small scale vegetable crop rotation*. Science of the Total Environment, 2013. **465**: p. 298-307.
6. Thangarajan, R., et al., *Effects of temperature and amendments on nitrogen mineralization in selected Australian soils*. Environmental Science and Pollution Research, 2013: p. 1-12.
7. Goldberg, E.D., *Black Carbon in the Environment: Properties and Distribution*. 1985, New York: John Wiley & Sons Inc. 216.
8. Kuhlbusch, T.A.J. and P.J. Crutzen, *Toward a global estimate of black carbon in residues of vegetation fires representing a sink of atmospheric CO₂ and a source of O₂*. Global Biogeochemical Cycles, 1995. **9**(4): p. 491-501.
9. Lehmann, J., *Bio-energy in the black*. Frontiers in Ecology and the Environment, 2007. **5**(7): p. 381-387.

- 567 10. Watson, A.Y. and P.A. Valberg, *Carbon black and soot: Two different substances*.
568 American Industrial Hygiene Association Journal, 2001. **62**(2): p. 218-228.
- 569 11. Knowles, O.A., et al., *Biochar for the mitigation of nitrate leaching from soil*
570 *amended with biosolids*. Science of the Total Environment, 2011. **409**(17): p. 3206-
571 3210.
- 572 12. Lehmann, J., G. John, and M. R., *Bio-char sequestration in terrestrial ecosystems - A*
573 *review*. Mitigation and Adaptation Strategies for Global Change, 2006. **11**(2): p. 403-
574 427.
- 575 13. Shafeeyan, M.S., et al., *Ammonia modification of activated carbon to enhance carbon*
576 *dioxide adsorption: Effect of pre-oxidation*. Applied Surface Science, 2011. **257**(9): p.
577 3936-3942.
- 578 14. Aguilar-Chávez, Á., et al., *Greenhouse gas emissions from a wastewater sludge-*
579 *amended soil cultivated with wheat (Triticum spp. L.) as affected by different*
580 *application rates of charcoal*. Soil Biology and Biochemistry, 2012. **52**: p. 90-95.
- 581 15. Cayuela, M., et al., *Biochar's role in mitigating soil nitrous oxide emissions: A review*
582 *and meta-analysis*. Agriculture, Ecosystems & Environment, 2014. **191**: p. 5-16.
- 583 16. Taghizadeh-Toosi, A., et al., *Biochar adsorbed ammonia is bioavailable*. Plant and
584 Soil, 2012. **350**(1-2): p. 57-69.
- 585 17. Mandal, S., et al., *Biochar-induced concomitant decrease in ammonia volatilization*
586 *and increase in nitrogen use efficiency by wheat*. Chemosphere, 2015.
- 587 18. Case, S.D.C., et al., *The effect of biochar addition on N₂O and CO₂ emissions from*
588 *a sandy loam soil - The role of soil aeration*. Soil Biology and Biochemistry, 2012.
589 **51**: p. 125-134.
- 590 19. Ding, Y., et al., *Evaluation of biochar effects on nitrogen retention and leaching in*
591 *multi-layered soil columns*. Water, Air, and Soil Pollution, 2010. **213**(1-4): p. 47-55.

- 592 20. Beck, D.A., G.R. Johnson, and G.A. Spolek, *Amending greenroof soil with biochar to*
593 *affect runoff water quantity and quality*. Environmental Pollution, 2011. **159**(8-9): p.
594 2111-2118.
- 595 21. Singh, B.P., et al., *Influence of biochars on nitrous oxide emission and nitrogen*
596 *leaching from two contrasting soils*. Journal of Environmental Quality, 2010. **39**(4): p.
597 1224-1235.
- 598 22. Ahmad, M., et al., *Speciation and phytoavailability of lead and antimony in a small*
599 *arms range soil amended with mussel shell, cow bone and biochar: EXAFS*
600 *spectroscopy and chemical extractions*. Chemosphere, 2014. **95**: p. 433-441.
- 601 23. Mohan, D., et al., *Organic and inorganic contaminants removal from water with*
602 *biochar, a renewable, low cost and sustainable adsorbent—a critical review*.
603 Bioresource technology, 2014. **160**: p. 191-202.
- 604 24. Rajapaksha, A.U., et al., *Invasive plant-derived biochar inhibits sulfamethazine*
605 *uptake by lettuce in soil*. Chemosphere, 2014. **111**: p. 500-504.
- 606 25. Vithanage, M., et al., *Sorption and transport of sulfamethazine in agricultural soils*
607 *amended with invasive-plant-derived biochar*. Journal of environmental management,
608 2014. **141**: p. 95-103.
- 609 26. Chan, K.Y., et al., *Using poultry litter biochars as soil amendments*. Australian
610 Journal of Soil Research, 2008. **46**(5): p. 437-444.
- 611 27. Laird, D.A., et al., *Impact of biochar amendments on the quality of a typical*
612 *Midwestern agricultural soil*. Geoderma, 2010. **158**(3-4): p. 443-449.
- 613 28. Chen, C.R., et al., *Impacts of greenwaste biochar on ammonia volatilisation from*
614 *bauxite processing residue sand*. Plant and Soil, 2013. **367**(1-2): p. 301-312.

29. Slavich, P., et al., *Contrasting effects of manure and green waste biochars on the properties of an acidic ferralsol and productivity of a subtropical pasture*. Plant and soil, 2013. **366**(1-2): p. 213-227.
30. Almaroai, Y.A., et al., *Effects of biochar, cow bone, and eggshell on Pb availability to maize in contaminated soil irrigated with saline water*. Environmental earth sciences, 2014. **71**(3): p. 1289-1296.
31. Moon, D.H., et al., *Immobilization of lead in contaminated firing range soil using biochar*. Environmental Science and Pollution Research, 2013. **20**(12): p. 8464-8471.
32. Zhou, Y., et al., *Biochar-supported zerovalent iron for removal of various contaminants from aqueous solutions*. Bioresource Technology, 2014. **152**: p. 538-542.
33. Martin, S.M., et al., *Marked changes in herbicide sorption–desorption upon ageing of biochars in soil*. Journal of hazardous materials, 2012. **231**: p. 70-78.
34. Zhang, M., et al., *Preparation and characterization of a novel magnetic biochar for arsenic removal*. Bioresource Technology, 2013. **130**: p. 457-462.
35. Clough, T.J., et al., *A Review of Biochar and Soil Nitrogen Dynamics*. Agronomy (Basel), 2013. **3**: p. 275-293.
36. Day, D., et al., *Economical CO₂, SO_x, and NO_x capture from fossil-fuel utilization with combined renewable hydrogen production and large-scale carbon sequestration*. Energy, 2005. **30**(14): p. 2558-2579.
37. Novak, J.M. and W.J. Busscher. *Evaluation of designer biochars to ameliorate select chemical and physical characteristics of degraded soils*. 2009.
38. IPCC, *Climate Change 2007: the physical science basis: contribution of Working Group I to the Fourth Assessment Report of the Intergovernmental Panel on Climate Change*, Cambridge Univ Pr. 2007.

39. Kalnay, E. and M. Cai, *Impact of urbanization and land-use change on climate*. Nature, 2003. **423**(6939): p. 528-531.
40. EPA, *Environmental guidelines, use and disposal of biosolid products*. NSW, Environmental Protection Authority, in NSW, Environmental Protection Authority. 1997: NSW.
41. Shahabadi, M.B., L. Yerushalmi, and F. Haghghat, *Impact of process design on greenhouse gas (GHG) generation by wastewater treatment plants*. Water research, 2009. **43**(10): p. 2679-2687.
42. IPCC, *Climate Change 1995, the Science of Climate Change. Contribution of Working Group I to the Second Assessment Report of the Intergovernmental Panel on Climate Change*. . 1996: Cambridge University Press, Cambridge, UK.
43. Frohking, S., et al., *Short- and long-term greenhouse gas and radiative forcing impacts of changing water management in Asian rice paddies*. Global Change Biology, 2004. **10**(7): p. 1180-1196.
44. Burgos, M., et al., *Anthropogenic effects on greenhouse gas (CH₄ and N₂O) emissions in the Guadalete River Estuary (SW Spain)*. Science of The Total Environment, 2015. **503**: p. 179-189.
45. Lemke, R.L., et al., *Can pulse crops play a role in mitigating greenhouse gases from North American agriculture?* Agronomy Journal, 2007. **99**(6): p. 1719-1725.
46. Jones, C.A. and R.D. Sands, *Impact of agricultural productivity gains on greenhouse gas emissions: A global analysis*. American Journal of Agricultural Economics, 2013: p. aat035.
47. Papageorgiou, A., J. Barton, and A. Karagiannidis, *Assessment of the greenhouse effect impact of technologies used for energy recovery from municipal waste: a case for England*. Journal of environmental management, 2009. **90**(10): p. 2999-3012.

- 665 48. Havlík, P., et al., *Climate change mitigation through livestock system transitions*.
666 Proceedings of the National Academy of Sciences, 2014. **111**(10): p. 3709-3714.
- 667 49. Burney, J. and V. Ramanathan, *Recent climate and air pollution impacts on Indian*
668 *agriculture*. Proceedings of the National Academy of Sciences, 2014. **111**(46): p.
669 16319-16324.
- 670 50. Gosain, A., S. Rao, and D. Basuray, *Climate change impact assessment on hydrology*
671 *of Indian river basins*. Current science, 2006. **90**(3): p. 346-353.
- 672 51. van Groenigen, K.J., C.W. Osenberg, and B.A. Hungate, *Increased soil emissions of*
673 *potent greenhouse gases under increased atmospheric CO₂*. Nature, 2011. **475**(7355):
674 p. 214-216.
- 675 52. Weber, C.L. and H.S. Matthews, *Food-miles and the relative climate impacts of food*
676 *choices in the United States*. Environmental science & technology, 2008. **42**(10): p.
677 3508-3513.
- 678 53. Brandao, M., L.M. i Canals, and R. Clift, *Soil organic carbon changes in the*
679 *cultivation of energy crops: Implications for GHG balances and soil quality for use in*
680 *LCA*. Biomass and Bioenergy, 2011. **35**(6): p. 2323-2336.
- 681 54. Jabro, J.D., et al., *Carbon dioxide flux as affected by tillage and irrigation in soil*
682 *converted from perennial forages to annual crops*. Journal of Environmental
683 Management, 2008. **88**(4): p. 1478-1484.
- 684 55. Al-Kaisi, M.M. and X. Yin, *Tillage and crop residue effects on soil carbon and*
685 *carbon dioxide emission in corn–soybean rotations*. Journal of Environmental
686 Quality, 2005. **34**(2): p. 437-445.
- 687 56. Syakila, A. and C. Kroeze, *The global nitrous oxide budget revisited*. Greenhouse Gas
688 Measurement and Management, 2011. **1**(1): p. 17-26.
- 689 57. Lehmann, J., *A handful of carbon*. Nature, 2007. **447**(7141): p. 143-144.

58. Kole, C., *Genomics and Breeding for Climate-Resilient Crops: Vol. 2 Target Traits*. 2013.
59. Paustian, K., et al., *CO₂ mitigation by agriculture: An overview*. Climatic Change, 1998. **40**(1): p. 135-162.
60. Wheeler, T. and J. Von Braun, *Climate change impacts on global food security*. Science, 2013. **341**(6145): p. 508-513.
61. Schimel, D.S., *Terrestrial biogeochemical cycles: Global estimates with remote sensing*. Remote Sensing of Environment, 1995. **51**(1): p. 49-56.
62. Lal, R., *Soil carbon sequestration impacts on global climate change and food security*. science, 2004. **304**(5677): p. 1623-1627.
63. Cayuela, M.L., S. Jeffery, and L. van Zwieten, *The molar H: C_{Org} ratio of biochar is a key factor in mitigating N₂O emissions from soil*. Agriculture, Ecosystems and Environment, 2015. **202**: p. 135-138.
64. Butterbach-Bahl, K., et al., *Nitrous oxide emissions from soils: how well do we understand the processes and their controls?* Philosophical Transactions of the Royal Society B: Biological Sciences, 2013. **368**(1621): p. 20130122.
65. Van Zwieten, L., et al., *An incubation study investigating the mechanisms that impact N₂O flux from soil following biochar application*. Agriculture, Ecosystems & Environment, 2014. **191**(0): p. 53-62.
66. Keith, A., B. Singh, and B.P. Singh, *Interactive priming of biochar and labile organic matter mineralization in a smectite-rich soil*. Environmental science & technology, 2011. **45**(22): p. 9611-9618.
67. Whitman, T., et al., *Priming effects in biochar-amended soils: implications of biochar-soil organic matter interactions for carbon storage*. Biochar for

714 Environmental Management: Science, Technology and Implementation, 2015: p. 455-
715 488.

716 68. Sarmah, A.K., et al., *Retention capacity of biochar-amended New Zealand dairy farm*
717 *soil for an estrogenic steroid hormone and its primary metabolite*. Soil Research,
718 2010. **48**(7): p. 648-658.

719 69. Rogovska, N., et al., *Impact of biochar on manure carbon stabilization and*
720 *greenhouse gas emissions*. Soil Science Society of America Journal, 2011. **75**(3): p.
721 871-879.

722 70. Quin, P., et al., *Biochar Changes Soil Structure and Water-Holding Capacity-A Study*
723 *with X-Ray Micro-Ct*. 한국토양비료학회 학술발표회 초록집, 2014: p. 121-121.

724 71. Hale, S.E., et al., *Quantifying the total and bioavailable polycyclic aromatic*
725 *hydrocarbons and dioxins in biochars*. Environmental science & technology, 2012.
726 **46**(5): p. 2830-2838.

727 72. Hilber, I., et al., *Quantitative determination of PAHs in biochar: a prerequisite to*
728 *ensure its quality and safe application*. Journal of agricultural and food chemistry,
729 2012. **60**(12): p. 3042-3050.

730 73. Maliszewska-Kordybach, B., et al., *Ecotoxic effect of phenanthrene on nitrifying*
731 *bacteria in soils of different properties*. Journal of environmental quality, 2007. **36**(6):
732 p. 1635-1645.

733 74. Guo, G.-X., et al., *Effect of long-term wastewater irrigation on potential*
734 *denitrification and denitrifying communities in soils at the watershed scale*.
735 Environmental science & technology, 2013. **47**(7): p. 3105-3113.

736 75. Spokas, K.A., *Review of the stability of biochar in soils: predictability of O: C molar*
737 *ratios*. Carbon Management, 2010. **1**(2): p. 289-303.

76. Shi, Y., L. Zhang, and M. Zhao, *Effect of Biochar Application on the Efficacy of the Nitrification Inhibitor Dicyandiamide in Soils*. BioResources, 2015. **10**(1): p. 1330-1345.
77. Cayuela, M.L., et al., *Biochar and denitrification in soils: when, how much and why does biochar reduce N₂O emissions?* Scientific reports, 2013. **3**.
78. Li, Y., et al., *Are the biogeochemical cycles of carbon, nitrogen, sulfur, and phosphorus driven by the "Fe^{III}-Fe^{II} redox wheel" in dynamic redox environments?* Journal of Soils and Sediments, 2012. **12**(5): p. 683-693.
79. Van Zwieten, L., et al., *Effects of biochar from slow pyrolysis of papermill waste on agronomic performance and soil fertility*. Plant and soil, 2010. **327**(1-2): p. 235-246.
80. DeLuca, T.H. and G.H. Aplet, *Charcoal and carbon storage in forest soils of the Rocky Mountain West*. Frontiers in Ecology and the Environment, 2008. **6**(1): p. 18-24.
81. Spokas, K.A., et al., *Impacts of woodchip biochar additions on greenhouse gas production and sorption/degradation of two herbicides in a Minnesota soil*. Chemosphere, 2009. **77**(4): p. 574-581.
82. Case, S.D.C., et al., *Can biochar reduce soil greenhouse gas emissions from a Miscanthus bioenergy crop?* GCB Bioenergy, 2014. **6**(1): p. 76-89.
83. Wu, F., et al., *Contrasting effects of wheat straw and its biochar on greenhouse gas emissions and enzyme activities in a Chernozemic soil*. Biology and Fertility of Soils, 2013. **49**(5): p. 555-565.
84. Singh, B.P., A.L. Cowie, and R.J. Smernik, *Biochar carbon stability in a clayey soil as a function of feedstock and pyrolysis temperature*. Environmental Science & Technology, 2012. **46**(21): p. 11770-11778.

- 762 85. Lehmann, J. and D. Solomon, *Organic carbon chemistry in soils observed by*
763 *synchrotron-based spectroscopy*. 2010. p. 289-312.
- 764 86. Clough, T.J. and L.M. Condron, *Biochar and the nitrogen cycle: Introduction*. Journal
765 of Environmental Quality, 2010. **39**(4): p. 1218-1223.
- 766 87. Spokas, K.A., et al., *Biochar: A Synthesis of Its Agronomic Impact beyond Carbon*
767 *Sequestration*. Journal of Environmental Quality, 2012. **41**(4): p. 973-989.
- 768 88. Ahmad, M., et al., *Biochar as a sorbent for contaminant management in soil and*
769 *water: a review*. Chemosphere, 2014. **99**: p. 19-33.
- 770 89. Zhou, Y., et al., *Sorption of heavy metals on chitosan-modified biochars and its*
771 *biological effects*. Chemical Engineering Journal, 2013. **231**: p. 512-518.
- 772 90. Mandal, S., et al., *Enhancement of chromate reduction in soils by surface modified*
773 *biochar*. Journal of environmental management, 2016.
- 774 91. Woolf, D., et al., *Sustainable biochar to mitigate global climate change*. Nature
775 Communications, 2010. **1**(5): p. 1-9.
- 776 92. Mukherjee, A. and A.R. Zimmerman, *Organic carbon and nutrient release from a*
777 *range of laboratory-produced biochars and biochar-soil mixtures*. Geoderma, 2013.
778 **193-194**: p. 122-130.
- 779 93. Gundale, M.J. and T.H. DeLuca, *Charcoal effects on soil solution chemistry and*
780 *growth of Koeleria macrantha in the ponderosa pine/Douglas-fir ecosystem*. Biology
781 and Fertility of Soils, 2007. **43**(3): p. 303-311.
- 782 94. Solomon, D., et al., *Molecular signature and sources of biochemical recalcitrance of*
783 *organic C in Amazonian Dark Earths*. Geochimica et Cosmochimica Acta, 2007.
784 **71**(9): p. 2285-2298.
- 785 95. Lehmann, J., et al., *Biochar effects on soil biota - A review*. Soil Biology and
786 Biochemistry, 2011. **43**(9): p. 1812-1836.

- 787 96. Lee, J.W., and Li, R., *Method for reducing CO₂, CO, NO_x and SO_x emission*. 2002:
788 United States.
- 789 97. Zimmerman, A.R., B. Gao, and M.-Y. Ahn, *Positive and negative carbon*
790 *mineralization priming effects among a variety of biochar-amended soils*. Soil
791 Biology and Biochemistry, 2011. **43**(6): p. 1169-1179.
- 792 98. Fuwape, J.A., *Charcoal and fuel value of agroforestry tree crops*. Agroforestry
793 Systems, 1993. **22**(3): p. 175-179.
- 794 99. Oyedun, A.O., K.L. Lam, and C.W. Hui, *Charcoal production via multistage*
795 *pyrolysis*. Chinese Journal of Chemical Engineering, 2012. **20**(3): p. 455-460.
- 796 100. Foley, G., *Charcoal making in developing countries*. 1986, International Institute for
797 Environmental and Development: Earthscan, UK. p. 124.
- 798 101. Streubel, J.D., et al., *Influence of contrasting biochar types on five soils at increasing*
799 *rates of application*. Soil Science Society of America Journal, 2011. **75**(4): p. 1402-
800 1413.
- 801 102. Zimmerman, A.R., *Abiotic and microbial oxidation of laboratory-produced black*
802 *carbon (biochar)*. Environmental science & technology, 2010. **44**(4): p. 1295-1301.
- 803 103. Díaz-Rojas, M., et al., *Effects of wastewater sludge, urea and charcoal on greenhouse*
804 *gas emissions in pots planted with wheat*. Applied Soil Ecology, 2014. **73**: p. 19-25.
- 805 104. Rashidi, N.A., S. Yusup, and B.H. Hameed, *Kinetic studies on carbon dioxide capture*
806 *using lignocellulosic based activated carbon*. Energy, 2013. **61**: p. 440-446.
- 807 105. Isoda, N., et al., *Optimization of preparation conditions of activated carbon from*
808 *agriculture waste utilizing factorial design*. Powder Technology, 2014. **256**: p. 175-
809 181.

- 810 106. Ioannidou, O. and A. Zabaniotou, *Agricultural residues as precursors for activated*
811 *carbon production—A review*. Renewable and Sustainable Energy Reviews, 2007.
812 **11**(9): p. 1966-2005.
- 813 107. Moreno-Castilla, C., et al., *Chemical and physical activation of olive-mill waste water*
814 *to produce activated carbons*. Carbon, 2001. **39**(9): p. 1415-1420.
- 815 108. Pevida, C., et al., *Surface modification of activated carbons for CO₂ capture*. Applied
816 Surface Science, 2008. **254**(22): p. 7165-7172.
- 817 109. Plaza, M.G., et al., *Application of thermogravimetric analysis to the evaluation of*
818 *aminated solid sorbents for CO₂ capture*. Journal of Thermal Analysis and
819 Calorimetry, 2008. **92**(2): p. 601-606.
- 820 110. Kuzyakov, Y., J.K. Friedel, and K. Stahr, *Review of mechanisms and quantification of*
821 *priming effects*. Soil Biology and Biochemistry, 2000. **32**(11-12): p. 1485-1498.
- 822 111. Kuzyakov, Y., *Priming effects: Interactions between living and dead organic matter*.
823 Soil Biology and Biochemistry, 2010. **42**(9): p. 1363-1371.
- 824 112. Whitman, T., et al., *Priming effects in biochar-amended soils: Implications of*
825 *biochar-soil organic matter interactions for carbon storage*. Biochar for
826 Environmental Management: Science, Technology and Implementation, 2015.
- 827 113. Chowdhury, S., *Nutrient Amendment and Carbon Sequestration in Soil* 2013,
828 University of South Australia. p. 144.
- 829 114. Luo, Y., et al., *Short term soil priming effects and the mineralisation of biochar*
830 *following its incorporation to soils of different pH*. Soil Biology and Biochemistry,
831 2011. **43**(11): p. 2304-2314.
- 832 115. Singh, B.P. and A.L. Cowie, *Long-term influence of biochar on native organic carbon*
833 *mineralisation in a low-carbon clayey soil*. Scientific reports, 2014. **4**: p. 3687.

- 834 116. Fang, Y., B. Singh, and B.P. Singh, *Effect of temperature on biochar priming effects*
835 *and its stability in soils*. Soil Biology and Biochemistry, 2015. **80**: p. 136-145.
- 836 117. Maestrini, B., P. Nannipieri, and S. Abiven, *A meta-analysis on pyrogenic organic*
837 *matter induced priming effect*. GCB Bioenergy, 2014.
- 838 118. Atkinson, C.J., J.D. Fitzgerald, and N.A. Hipps, *Potential mechanisms for achieving*
839 *agricultural benefits from biochar application to temperate soils: a review*. Plant and
840 soil, 2010. **337**(1-2): p. 1-18.
- 841 119. Jeffery, S., et al., *A quantitative review of the effects of biochar application to soils on*
842 *crop productivity using meta-analysis*. Agriculture, ecosystems & environment, 2011.
843 **144**(1): p. 175-187.
- 844 120. Ippolito, J.A., et al., *Biochar elemental composition and factors influencing nutrient*
845 *retention*. Biochar for Environmental Management: Science, Technology and
846 Implementation, 2015: p. 139.
- 847 121. Liang, B., et al., *Black carbon increases cation exchange capacity in soils*. Soil
848 Science Society of America Journal, 2006. **70**(5): p. 1719-1730.
- 849 122. Laird, D.A., et al., *Review of the pyrolysis platform for coproducing bio-oil and*
850 *biochar*. Biofuels, Bioproducts and Biorefining, 2009. **3**(5): p. 547-562.
- 851 123. Wardle, D.A., M.C. Nilsson, and O. Zackrisson, *Response to comment on "fire-*
852 *derived charcoal causes loss of forest humus"*. Science, 2008. **321**(5894).
- 853 124. Lehmann, J., et al., *Australian climate-carbon cycle feedback reduced by soil black*
854 *carbon*. Nature Geoscience, 2008. **1**(12): p. 832-835.
- 855 125. Joseph, S., et al., *Shifting paradigms: development of high-efficiency biochar*
856 *fertilizers based on nano-structures and soluble components*. Carbon Management,
857 2013. **4**(3): p. 323-343.

- 858 126. Novak, J.M., et al., *Designing relevant biochars as soil amendments using*
859 *lignocellulosic-based and manure-based feedstocks*. Journal of soils and sediments,
860 2014. **14**(2): p. 330-343.
- 861 127. Chen, B., Z. Chen, and S. Lv, *A novel magnetic biochar efficiently sorbs organic*
862 *pollutants and phosphate*. Bioresource technology, 2011. **102**(2): p. 716-723.
- 863 128. Jing, X.R., et al., *Enhanced adsorption performance of tetracycline in aqueous*
864 *solutions by methanol-modified biochar*. Chemical Engineering Journal, 2014. **248**: p.
865 168-174.
- 866 129. Paaanen, A., et al., *Sorption of cobalt on activated carbons from aqueous solutions*.
867 Separation science and technology, 1997. **32**(1-4): p. 813-826.
- 868 130. Rehrah, D., et al., *Production and characterization of biochars from agricultural by-*
869 *products for use in soil quality enhancement*. Journal of Analytical and Applied
870 Pyrolysis, 2014. **108**: p. 301-309.
- 871 131. Novak, J., K. Cantrell, and D. Watts, *Compositional and thermal evaluation of*
872 *lignocellulosic and poultry litter chars via high and low temperature pyrolysis*.
873 Bioenergy Research, 2013. **6**(1): p. 114-130.
- 874 132. Treacy, M.M.J., T.W. Ebbesen, and J.M. Gibson, *Exceptionally high Young's modulus*
875 *observed for individual carbon nanotubes*. Nature, 1996. **381**(6584): p. 678-680.
- 876 133. Lourie, O. and H.D. Wagner, *Evaluation of Young's modulus of carbon nanotubes by*
877 *micro-Raman spectroscopy*. Journal of Materials Research, 1998. **13**(9): p. 2418-
878 2422.
- 879 134. Johns, M.M., W.E. Marshall, and C.A. Toles, *The effect of activation method on the*
880 *properties of pecan shell-activated carbons*. Journal of chemical technology and
881 biotechnology, 1999. **74**(11): p. 1037-1044.

- 882 135. Kim, J.-W., et al., *Production of granular activated carbon from waste walnut shell*
883 *and its adsorption characteristics for Cu²⁺ ion*. Journal of hazardous materials,
884 2001. **85**(3): p. 301-315.
- 885 136. Atkinson, J.D., et al., *Synthesis and characterization of iron-impregnated porous*
886 *carbon spheres prepared by ultrasonic spray pyrolysis*. Carbon, 2011. **49**(2): p. 587-
887 598.
- 888 137. Agrafioti, E., et al., *Biochar production by sewage sludge pyrolysis*. Journal of
889 Analytical and Applied Pyrolysis, 2013. **101**: p. 72-78.
- 890 138. Agrafioti, E.D.K.a.E.D., *Ca and Fe modified biochars as adsorbents of arsenic and*
891 *chromium in aqueous solutions*. Journal of Environmental Management, 2014.
- 892 139. Yao, Y., et al., *Removal of phosphate from aqueous solution by biochar derived from*
893 *anaerobically digested sugar beet tailings*. Journal of Hazardous Materials, 2011.
894 **190**(1-3): p. 501-507.
- 895 140. Inyang, M., et al., *Removal of heavy metals from aqueous solution by biochars*
896 *derived from anaerobically digested biomass*. Bioresource Technology, 2012. **110**: p.
897 50-56.
- 898 141. Wang, M.C., G.D. Sheng, and Y.P. Qiu, *A novel manganese-oxide/biochar composite*
899 *for efficient removal of lead(II) from aqueous solutions*. International Journal of
900 Environmental Science and Technology, 2014: p. 1-8.
- 901 142. Qian, K., et al., *Recent advances in utilization of biochar*. Renewable and Sustainable
902 Energy Reviews, 2015. **42**(0): p. 1055-1064.
- 903 143. Tsang, S.C., et al., *A simple chemical method of opening and filling carbon*
904 *nanotubes*. Nature, 1994. **372**(6502): p. 159-162.

- 905 144. Satishkumar, B.C., et al., *Novel experiments with carbon nanotubes: Opening, filling,*
906 *closing and functionalizing nanotubes.* Journal of Physics B: Atomic, Molecular and
907 Optical Physics, 1996. **29**(21): p. 4925-4934.
- 908 145. Yu, Z. and L.E. Brus, *Reversible oxidation effect in raman scattering from metallic*
909 *single-wall carbon nanotubes.* Journal of Physical Chemistry A, 2000. **104**(47): p.
910 10998-10999.
- 911 146. Hernadi, K., et al., *Reactivity of different kinds of carbon during oxidative purification*
912 *of catalytically prepared carbon nanotubes.* Solid State Ionics, 2001. **141-142**: p. 203-
913 209.
- 914 147. Martínez-Hernández, A.L., C. Velasco-Santos, and V.M. Castaño, *Carbon nanotubes*
915 *composites: Processing, grafting and mechanical and thermal properties.* Current
916 Nanoscience, 2010. **6**(1): p. 12-39.
- 917 148. Lou, X., et al., *Grafting of alkoxyamine end-capped (co)polymers onto multi-walled*
918 *carbon nanotubes.* Polymer, 2004. **45**(18): p. 6097-6102.
- 919 149. Paul, A., B.P. Grady, and W.T. Ford, *Polystyrene composites of single-walled carbon*
920 *nanotubes-graft-polystyrene.* Polymer International, 2012. **61**(11): p. 1603-1610.
- 921 150. Yong, S.K., et al., *Sulfur-containing chitin and chitosan derivatives as trace metal*
922 *adsorbents: A review.* Critical Reviews in Environmental Science and Technology,
923 2013. **43**(16): p. 1741-1794.
- 924 151. Liu, P., *Modifications of carbon nanotubes with polymers.* European Polymer Journal,
925 2005. **41**(11): p. 2693-2703.
- 926 152. Olek, M., M. Hilgendorff, and M. Giersig, *A simple route for the attachment of*
927 *colloidal nanocrystals to noncovalently modified multiwalled carbon nanotubes.*
928 Colloids and Surfaces A: Physicochemical and Engineering Aspects, 2007. **292**(1): p.
929 83-85.

- 930 153. Chatterjee, S., S.R. Lim, and S.H. Woo, *Removal of Reactive Black 5 by zero-valent*
931 *iron modified with various surfactants*. Chemical Engineering Journal, 2010. **160**(1):
932 p. 27-32.
- 933 154. Yao, Y., et al., *Effect of biochar amendment on sorption and leaching of nitrate,*
934 *ammonium, and phosphate in a sandy soil*. Chemosphere, 2012. **89**(11): p. 1467-
935 1471.
- 936 155. Xue, Y., et al., *Hydrogen peroxide modification enhances the ability of biochar*
937 *(hydrochar) produced from hydrothermal carbonization of peanut hull to remove*
938 *aqueous heavy metals: Batch and column tests*. Chemical Engineering Journal, 2012.
939 **200-202**: p. 673-680.
- 940 156. Joseph, S.D., et al., *An investigation into the reactions of biochar in soil*. Australian
941 Journal of Soil Research, 2010. **48**(6-7): p. 501-515.
- 942 157. Lehmann, J. and S. Joseph, *Biochar for environmental management: science and*
943 *technology*. 2009: Earthscan.
- 944 158. Antal, M.J. and M. Grønli, *The art, science, and technology of charcoal production*.
945 Industrial & Engineering Chemistry Research, 2003. **42**(8): p. 1619-1640.
- 946 159. Glaser, B., J. Lehmann, and W. Zech, *Ameliorating physical and chemical properties*
947 *of highly weathered soils in the tropics with charcoal—a review*. Biology and fertility
948 of soils, 2002. **35**(4): p. 219-230.
- 949 160. Gómez-Luna, B.E., et al., *Charcoal production at kiln sites affects C and N dynamics*
950 *and associated soil microorganisms in Quercus spp. temperate forests of central*
951 *Mexico*. Applied Soil Ecology, 2009. **41**(1): p. 50-58.
- 952 161. Vázquez-Marrufo, G., et al., *Microsite soil changes associated with traditional*
953 *charcoal production in Quercus temperate forest in central Mexico*. Phytion, 2003. **72**:
954 p. 85-99.

- 955 162. Czakkel, O., et al., *Drying of resorcinol-formaldehyde gels with CO₂ medium*.
956 Microporous and Mesoporous Materials, 2012. **148**(1): p. 34-42.
- 957 163. Di Lonardo, S., et al., *Biochar successfully replaces activated charcoal for in vitro*
958 *culture of two white poplar clones reducing ethylene concentration*. Plant Growth
959 Regulation, 2013. **69**(1): p. 43-50.
- 960 164. Foo, K. and B. Hameed, *An overview of landfill leachate treatment via activated*
961 *carbon adsorption process*. Journal of Hazardous Materials, 2009. **171**(1): p. 54-60.
- 962 165. Awadallah-F, A. and S.A. Al-Muhtaseb, *Carbon dioxide sequestration and methane*
963 *removal from exhaust gases using resorcinol-formaldehyde activated carbon xerogel*.
964 Adsorption, 2013. **19**(5): p. 967-977.
- 965 166. Masiello, C. and E. Druffel, *Black carbon in deep-sea sediments*. Science, 1998.
966 **280**(5371): p. 1911-1913.
- 967 167. Ni, M., et al., *A review on black carbon emissions, worldwide and in China*.
968 Chemosphere, 2014. **107**: p. 83-93.
- 969 168. Koelmans, A.A., et al., *Black carbon: The reverse of its dark side*. Chemosphere,
970 2006. **63**(3): p. 365-377.
- 971 169. Cheng, C.-H., et al., *Oxidation of black carbon by biotic and abiotic processes*.
972 Organic Geochemistry, 2006. **37**(11): p. 1477-1488.
- 973 170. Mukherjee, A., R. Lal, and A.R. Zimmerman, *Effects of biochar and other*
974 *amendments on the physical properties and greenhouse gas emissions of an*
975 *artificially degraded soil*. Science of The Total Environment, 2014. **487**(0): p. 26-36.
- 976 171. Nelissen, V., et al., *Effect of different biochar and fertilizer types on N₂O and NO*
977 *emissions*. Soil Biology and Biochemistry, 2014. **70**(0): p. 244-255.

978 172. Verhoeven, E. and J. Six, *Biochar does not mitigate field-scale N₂O emissions in a*
979 *Northern California vineyard: An assessment across two years*. Agriculture,
980 Ecosystems & Environment, 2014. **191**(0): p. 27-38.

981 173. Harter, J., et al., *Linking N₂O emissions from biochar-amended soil to the structure*
982 *and function of the N-cycling microbial community*. ISME Journal, 2014. **8**(3): p. 660-
983 674.

984 174. Fungo, B., et al., *N₂O and CH₄ emission from soil amended with steam-activated*
985 *biochar*. Journal of Plant Nutrition and Soil Science, 2014. **177**(1): p. 34-38.

986 175. Case, S.D.C., et al., *Biochar suppresses N₂O emissions while maintaining N*
987 *availability in a sandy loam soil*. Soil Biology and Biochemistry, 2015. **81**: p. 178-
988 185.

989 176. Lin, X.W., et al., *Effects of biochar application on greenhouse gas emissions, carbon*
990 *sequestration and crop growth in coastal saline soil*. European Journal of Soil
991 Science, 2015. **66**(2): p. 329-338.

992 177. Van Zwieten, L., et al., *Pyrolysing poultry litter reduces N₂O and CO₂ fluxes*.
993 Science of The Total Environment, 2013. **465**(0): p. 279-287.

994 178. Angst, T.E., et al., *Impact of pine chip biochar on trace greenhouse gas emissions and*
995 *soil nutrient dynamics in an annual ryegrass system in California*. Agriculture,
996 Ecosystems & Environment, 2014. **191**(0): p. 17-26.

997 179. Shen, J., et al., *Contrasting effects of straw and straw-derived biochar amendments on*
998 *greenhouse gas emissions within double rice cropping systems*. Agriculture,
999 Ecosystems & Environment, 2014. **188**(0): p. 264-274.

1000 180. Watanabe, A., et al., *Five crop seasons' records of greenhouse gas fluxes from upland*
1001 *fields with repetitive applications of biochar and cattle manure*. Journal of
1002 Environmental Management, 2014. **144**(0): p. 168-175.

- 1003 181. Zhu, K., et al., *The different effects of applying fresh, composted or charred manure*
1004 *on soil N₂O emissions*. Soil Biology and Biochemistry, 2014. **74**: p. 61-69.
- 1005 182. Schimmelpfennig, S., et al., *Biochar, hydrochar and uncarbonized feedstock*
1006 *application to permanent grassland—Effects on greenhouse gas emissions and plant*
1007 *growth*. Agriculture, Ecosystems & Environment, 2014. **191**(0): p. 39-52.
- 1008 183. Castaldi, S., et al., *Impact of biochar application to a Mediterranean wheat crop on*
1009 *soil microbial activity and greenhouse gas fluxes*. Chemosphere, 2011. **85**(9): p.
1010 1464-1471.
- 1011 184. Xie, Z., et al., *Impact of biochar application on nitrogen nutrition of rice,*
1012 *greenhouse-gas emissions and soil organic carbon dynamics in two paddy soils of*
1013 *China*. Plant and soil, 2013. **370**(1-2): p. 527-540.
- 1014 185. Sackett, T.E., et al., *Soil and greenhouse gas responses to biochar additions in a*
1015 *temperate hardwood forest*. GCB Bioenergy, 2014.
- 1016 186. Bell, M.J. and F. Worrall, *Charcoal addition to soils in NE England: A carbon sink*
1017 *with environmental co-benefits?* Science of The Total Environment, 2011. **409**(9): p.
1018 1704-1714.
- 1019 187. Kimetu, J.M., et al., *Using activated biochar for greenhouse gas mitigation and*
1020 *industrial water treatment*. Mitigation and Adaptation Strategies for Global Change,
1021 2014: p. 1-17.
- 1022 188. Hosseini, S., et al., *Adsorption of carbon dioxide using activated carbon impregnated*
1023 *with Cu promoted by zinc*. Journal of the Taiwan Institute of Chemical Engineers,
1024 2015. **52**: p. 109-117.
- 1025 189. Heidari, A., et al., *Evaluation of CO₂ adsorption with eucalyptus wood based*
1026 *activated carbon modified by ammonia solution through heat treatment*. Chemical
1027 Engineering Journal, 2014. **254**: p. 503-513.

- 1028 190. Zhang, M., et al., *Synthesis, characterization, and environmental implications of*
1029 *graphene-coated biochar*. Science of the Total Environment, 2012. **435-436**: p. 567-
1030 572.
- 1031 191. Rajapaksha, A.U., et al., *Enhanced sulfamethazine removal by steam-activated*
1032 *invasive plant-derived biochar*. Journal of hazardous materials, 2015. **290**: p. 43-50.
- 1033 192. Vithanage, M., et al., *Acid-activated biochar increased sulfamethazine retention in*
1034 *soils*. Environmental Science and Pollution Research, 2014: p. 1-12.
- 1035 193. Shen, B., et al., *Elemental mercury removal by the modified bio-char from medicinal*
1036 *residues*. Chemical Engineering Journal, 2015. **272**: p. 28-37.
- 1037 194. Yang, G.-X. and H. Jiang, *Amino modification of biochar for enhanced adsorption of*
1038 *copper ions from synthetic wastewater*. Water Research, 2014. **48**: p. 396-405.
- 1039 195. Liu, P., et al., *Modification of bio-char derived from fast pyrolysis of biomass and its*
1040 *application in removal of tetracycline from aqueous solution*. Bioresource
1041 Technology, 2012. **121**: p. 235-240.
- 1042 196. Jung, K.-W., et al., *A novel approach for preparation of modified-biochar derived*
1043 *from marine macroalgae: Dual purpose electro-modification for improvement of*
1044 *surface area and metal impregnation*. Bioresource Technology, 2015. **191**: p. 342-
1045 345.
- 1046 197. Wang, S., et al., *Manganese oxide-modified biochars: Preparation, characterization,*
1047 *and sorption of arsenate and lead*. Bioresource Technology, 2015. **181**: p. 13-17.
- 1048 198. Zhang, M.M., et al., *Chitosan modification of magnetic biochar produced from*
1049 *Eichhornia crassipes for enhanced sorption of Cr(vi) from aqueous solution*. RSC
1050 Advances, 2015. **5(58)**: p. 46955-46964.

- 1051 199. Lee, B.-K. and M.-V. Nguyen, *Cu²⁺ ion adsorption from aqueous solutions by amine*
1052 *activated poultry manure biochar*. Journal of Selcuk University Natural and Applied
1053 Science, 2014: p. 877-884.
- 1054 200. Usman, A.R., et al., *Chemically modified biochar produced from conocarpus waste*
1055 *increases NO₃ removal from aqueous solutions*. Environmental geochemistry and
1056 health, 2015: p. 1-11.
- 1057 201. De, M., et al., *Mercury removal by bio-char based modified activated carbons*. Fuel,
1058 2013. **103**: p. 570-578.
- 1059 202. Dastgheib, S.A. and D.A. Rockstraw, *Pecan shell activated carbon: synthesis,*
1060 *characterization, and application for the removal of copper from aqueous solution*.
1061 Carbon, 2001. **39**(12): p. 1849-1855.
- 1062 203. Puziy, A., et al., *Synthetic carbons activated with phosphoric acid: I. Surface*
1063 *chemistry and ion binding properties*. Carbon, 2002. **40**(9): p. 1493-1505.
- 1064 204. Vargas, A.M., et al., *Preparation and characterization of activated carbon from a*
1065 *new raw lignocellulosic material: Flamboyant (Delonix regia) pods*. Journal of
1066 environmental management, 2011. **92**(1): p. 178-184.
- 1067 205. Park, J., et al., *Activated carbon from biochar: Influence of its physicochemical*
1068 *properties on the sorption characteristics of phenanthrene*. Bioresource technology,
1069 2013. **149**: p. 383-389.
- 1070 206. Król, M., G. Gryglewicz, and J. Machnikowski, *KOH activation of pitch-derived*
1071 *carbonaceous materials—Effect of carbonization degree*. Fuel Processing
1072 Technology, 2011. **92**(1): p. 158-165.
- 1073 207. Zhang, M. and B. Gao, *Removal of arsenic, methylene blue, and phosphate by*
1074 *biochar/AlOOH nanocomposite*. Chemical Engineering Journal, 2013. **226**: p. 286-
1075 292.

1076 208. Bolan, N.S., L. Wong, and D. Adriano, *Nutrient removal from farm effluents*.
1077 Bioresource technology, 2004. **94**(3): p. 251-260.

1078

1079

1080

1081

1082

1083

1084

1085

1086

1087

1088

1089

1090

1091

1092

1093

Product name	Raw materials/feed stock	Manufacture conditions (temperature/ time/ environment)	Size/shape/colour	Key properties/application	References
Biochar	A range of organic biomasses (plant residues, animal manures, waste materials etc.)	Temperature range: from 100 to below 800 °C (using pyrolyzer unit) Environment: N ₂ gas and reduced oxygen condition Time: Both slow and fast pyrolysis	Black in color	<ul style="list-style-type: none"> Improved characteristics such as high surface area, pore volume, surface functional groups Supply macro and micronutrients for plant growth Reduce heavy metal toxicity Improve soil physical, chemical, and biological properties 	[22, 156, 157]
Charcoal	Wood and other substance (animal and vegetable substance)	Temperature range: general range from 200 to < 700 °C Peak temperature: between 500 to 600 °C Environment: reduced oxygen condition Time: slow pyrolysis (12 to 14 days sometimes)	Light and black residue	<ul style="list-style-type: none"> Act as a potential adsorptive material Improve plant growth and development Act as a soil conditioner Positively affect seed germination, plant growth, and yield 	[158-161]
AC	Chemical, physical, and heating of various carbonaceous materials	Temperature: High temperature (> 500 °C to 1000 °C) Time: > 10 h Activation: Steam/ CO ₂ , polymerization of hydroxylated benzene and aldehyde in a solvent, chemical activation includes HNO ₃ , H ₂ SO ₄ , NaOH, KOH, synthesis of a resorcinol- formaldehyde xerogel at specific condition to form AC	100µm to 600 µm, black in colour	<ul style="list-style-type: none"> Improved physicochemical properties (surface area, extensive internal pore structure) It can be used in various industries (pharmaceuticals, mining, chemical, petroleum etc.) because of its high adsorptive properties Remove organic and inorganic species from industrial effluent Remove pesticides from drinking water 	[106, 162-165]

		xerogel			
Black carbon	An organic material ranges from slightly charred biomass to charcoal. It is chemically heterogeneous, biologically refractory class of carbon compound	Temperature: incomplete combustion of plant biomass, fossil fuel and biofuel (muffle furnace) Environment: Open burning Time: >8 h	Fine particulate matter ($PM \geq 2.5 \mu m$)	<ul style="list-style-type: none"> • High specific surface area • Increase soil fertility by supplying a range of nutrients • It can cause serious health problem by carrying carcinogenic compounds 	[166-169]

1095 *AC: Activated carbon*

1096

1097

1098

1099

1100

1101 Table 2: Effect of biochar (BC) on greenhouse gas (GHG) mitigation and soil health

Stock material	Biochar application rate (ton/ha)	Pyrolysis temperature (°C)	Effect on GHG emission (N ₂ O/NH ₃ /CO ₂ /CH ₄)	Nutrient retention/soil health	References
Poultry manure and stem wood	15	400 and 550	All BC application reduced N ₂ O emission up to 73% due to increased sorptive capacity of biochars	Nutrient sorptive properties of biochar decreased NO ₃ leaching and conserved N in the soil	[21]
Oakwood	5.5	650	Cumulative emissions of CH ₄ , CO ₂ , and N ₂ O from biochar amended soils were reduced by 56, 92 and 43% respectively	BC application significantly increased soil C by 7%, increased surface area of soil by 15% and reduced bulk density by 13%	[170]
Willow, pine, maize and wood mixture (Spruce, Silver fir, Scots pine, Beech, Oak)	20	350, 450, 480, 550 and 650	Decreased N ₂ O emission by 52% with BC treatment (on average)	BC application decreased N availability through biotic and abiotic immobilization processes	[171]
Walnut shell and pine chip biochar	10	Pine chip at 550 and wall nutshell at 900	BC application increased N ₂ O emission (2.0 kg/ha N ₂ O/yr for control and 4.14 kg/ha N ₂ O/yr for BC)	Soil pH increased up to 0.5 to 1 unit, combination of increased N supply and increased rates of nitrification and denitrification	[172]
Green waste biochar	0 and 24	700	N ₂ O emission reduced up to 96% with 10% BC application and 47% with 2% BC	BC application enhanced microbial N ₂ O reduction and increased the abundance of microorganisms for N ₂ -fixation	[173]

Maize stover and eucalyptus wood	15	350 and 550	BC application reduced N ₂ O emission up to 10 to 41% and increased CH ₄ emission up to 14-70%	Steam activated BC affect soil pH-buffer capacity, specific chemical toxins, metal complexes and precipitation produces resulting from BC application	[174]
Oil seed rape and wheat	28	400	Cumulative soil N ₂ O production reduced by 91% and reduced cumulative denitrification by 37% with BC	BC application increased mineralization/nitrification, reduced denitrification and induced inorganic N immobilization	[175]
Cornstalk biochar	0, 3.2, 16 and 32	400	Increased N ₂ O emissions by 17.5%, 92.3% biochar carbon and 16.8% of corn stalk carbon sequestered into the soil within 1 year	BC application increased soybean biomass up to 24% and wheat 32%	[176]
Poultry litter biochar	10	550	BC along with urea reduced N ₂ O emission up to 69.4%	BC application with urea increased N uptake by corn plant, also increased plant available P and pH	[177]
Pine chip	5.7 and 18.8	550	Biochar application reduced N ₂ O emission by 15.7% and CH ₄ emission by 38.6%	Carbon content was increased about 74%. Soil properties like pH, CEC, N mineralization also increased with biochar application	[178]
Rice straw	7.5, 22.5, 24 and 48	-	N ₂ O emission increased by 0.13 to 0.80 times but CH ₄ emission reduced with biochar addition	Biochar application increased rice yield during two growing seasons	[179]

Hardwood (Oak, cherry, and ash)	50	400	Biochar application suppressed soil CO ₂ emissions by 52% and net soil CO ₂ eq. emissions by 55% but showed no significant reduction in N ₂ O emissions	Biochar application increased carbon used efficiency and bioenergy crop production due to GHG balance	[82]
Bamboo char	20	700-800	Biochar application affects N ₂ O and CO ₂ emissions significantly throughout two years of cropping	Biochar with cow manure plot increased crop production by 110% in 2009 and 160-180% in 2010	[180]
Pig manure	1.2	550	Biochar with compost application reduced N ₂ O emissions by 41% and increased cumulative CO ₂ emissions by 31-45%	Biochar application increased C:N ratio, total C, and P	[181]
<i>Miscanthus × giganteus</i> straw	9.3	550-600	Biochar application had no effect on CO ₂ emission but it reduced N ₂ O emissions by 54%	Biochar application increased soil pH and showed significant positive effect on growth of forbs	[182]
Beech, hazel, birch and oak	33 and 66	500	BC application reduced N ₂ O emission from 76% to 26% but no significant difference observed for CH ₄ emission	Increased soil pH but there is no significant improvement of mineral N content after adding BC, also there is no negative impact on soil microorganisms	[183]
Macadamia nutshell and poultry litter	25	460 and 550	Poultry litter BC reduced NH ₃ volatilization up to 70%	Increased N uptake capacity of wheat plant up to 76% with poultry litter BC	[17]

Wheat straw and corn stalk	13.22	250, 300, 350 and 400	Negative impact on GHG emission. BC application significantly increased N ₂ O emission but it reduced CH ₄ emission to some extent	No significant increase in rice yield with BC application and only 2% of BC N was available for plant uptake but it increased C and N content of soils	[184]
Wheat straw	0, 10 and 25	450	Reduced N ₂ O emission up to 55% with 10 ton/ha BC and 96% with 25t/ha BC application. No significant effect on CO ₂ emission	Activity of urease enzyme was increased with BC application compared to dehydrogenase and β -glycosidase	[83]
Maple and spruce sawdust	5	350 and 450	No significant treatment effects on fluxes of GHG (CO ₂ , CH ₄ , N ₂ O) were observed in the field	BC application increased limited plant nutrients like P and Ca	[185]

1102 BC: Biochar; GHG: Greenhouse gas

1103 Table 3: Effect of charcoal and activated carbon (AC) on greenhouse gas (GHG) emissions

Char material	Stock material	Pyrolysis temperature (°C)	Effect on GHG emission (N ₂ O/NH ₃ /CO ₂ /CH ₄)	References
Charcoal	Wood	200 – 300	≥ 1.5% application of charcoal reduced CO ₂ emission ≥ 37% and N ₂ O by 44% when 4.5% was the application rate	[14]
Charcoal	Wood	>200	There is no significant effect of adding charcoal on GHG mitigation	[103]
Charcoal	Coconut shell	450	There is no significant effect on CO ₂ mitigation but it can mitigate N ₂ O & CH ₄ emission	[81]

Charcoal	Lump-wood	450	Decreased nitrate leaching significantly and increased CO ₂ emission while the rate of charcoal application was higher also increased losses of C	[186]
Charcoal	Organic residue, wood	200 and 300	Lowest C mineralization was observed after charcoal treatment and there was no effect of charcoal on N ₂ O emission	[160]
Ammonia modified AC	Palm shell based granular AC	Ammonia modification with pre-oxidation- air introduced at 400	CO ₂ adsorption by AC increased with pre-heat treated aminated samples	[13]
AC	Agricultural waste like coconut shell, coconut fibre, rice husk, plan mesocarp fibre and plan kernel shell	Waste materials were synthesised in a vertical pyrolysis reactor	Adsorption of CO ₂ by AC increased and it's greatly varied with factors like temperature, precursors products and particle size	[104]
AC	Steam AC made from lignite coal	300	Activated biochar has higher affinity to organics and removed 75% of TOC from steam-assisted-gravity-drainage	[187]
AC	Pre-treatment was done by HNO ₃ and later AC impregnated with Cu(NO ₃) ₂ and ZnSO ₄	AC was purchased and impregnated AC was dried at 110	Impregnated AC increased CO ₂ adsorption up to 49% when 20% Cu/Zn was loaded on AC	[188]
AC from eucalyptus wood	AC was functionalised with pure gaseous ammonia	Carbonisation temperature was 450	Incorporation of N groups in AC due to functionalization increased its CO ₂ adsorption capacity	[189]

1104 AC: Activated carbon; GHG: Greenhouse gas

1105

1106

Stock material	Pyrolysis temperature (°C)	Modification	Effect of char modification	References
Bamboo, sugarcane bagasse, hickory wood and peanut hull	600	Chitosan (naturally abundant polysaccharide) used for modification	Chitosan modified BC removed 150% more Pb, 316% more Cd and 233% more Cu than unmodified BC	[89]
Bamboo	600	Chitosan used as an organic glue to attach zerovalent iron onto BC surface	ZVI coated BC increased removal of Pb(II) from 23.9% to 59.6% and Cr (VI) from 0% to 27.8% from aqueous solution	[32]
Cottonwood	600	Synthetic graphite powder, methylene blue and 1, 3, 6, 8-pyrenetetrasulfonic acid (Py-SO ₃) tetrasodium salt hydrate were used to coat BC	Graphene-coated BC improved adsorption of PAH by 20 times than untreated BC	[190]
Peanut hull	300	Hydrogen peroxide (H ₂ O ₂) used to modify BC	Increased oxygen-containing functional group of BC like carboxylic group and enhanced Pb sorption ability 20 times more than untreated BC	[155]
Cottonwood	600	Biomass was pre-treated with FeCl ₃ .6H ₂ O to produce BC/γ Fe ₂ O ₃	Modified BC has excellent ferromagnetic properties which have strong sorption ability to aqueous As	[34]
Rice husk	300	Ca ²⁺ as CaO, Fe ⁰ as iron powder and Fe ³⁺ as FeCl ₃ .6H ₂ O were used to modify BC	Modified BC with Ca ²⁺ and Fe ³⁺ showed higher As adsorption capacity (>95%), on the other hand, Fe ⁰ showed only 58%, but the Cr adsorption was not so high as As	[138]
Tea waste	300 & 700	Steam activation was used to modify BC Samples were treated with 5 mL min ⁻¹ of steam for an additional 45 min under the peak temperature	Steam activated BC produced at 700 °C showed the highest sulfamethazine sorption among all BCs studied due to its largest surface area and pore volume	[24]

Invasive plant (Burcucumber)	300 & 700	Steam activation was used to modify BC Samples were treated with 5 mL min ⁻¹ of steam for an additional 45 min under the peak temperature	The steam activated BC produced at 700 °C showed 55% increase in sorption capacity of sulfamethazine compared to that of non-activated BC produced at the same temperature	[191]
Invasive plant (Burcucumber)	700	BCs were activated with 30% sulphuric and oxalic acids	Modified BC showed an extensive increase in the BET surface area and enhancement in the sorption of sulfamethazine	[192]
Raw medicinal residue from a Chinese herb pharmaceutical factory	600 because this temperature is optimum when the Hg removal capacity was considered	Physical activation involved quartz tube reactor and then physically activated BC used for chemical activation by using HCl, ZnCl ₂ , and NH ₄ Cl through impregnation	Modification improved physicochemical properties of BC and increased removal rate of elemental Hg from fuel gas. Also its considered as a cost effective sorbent with high activity	[193]
Pristine (sawdust char)	500 (fast pyrolysis)	Amino modification involved H ₂ SO ₄ and HNO ₃ . Desired product was dried overnight at 90 °C	Modification increased Cu(II) adsorption capacity of BC from water solution. The Cu(II) combined with the amino groups through surface complexation	[194]
Rick husk	450-500 (fast pyrolysis)	Raw BC was modified by specified acid (H ₂ SO ₄) and alkali (KOH). Final wet BC was dried at 80 °C for 12h and termed as acid BC and alkali bio-char	Alkali BC increased tetracyclic adsorption capacity (58.8 mg/g). Also, modified BC has graphite-like structure, higher surface area, pore volume and these properties of BC plays an important role in TC adsorption	[195]
Brown marine macroalgae	450 under N ₂ flow for 2 h	Electro modification was performed by using aluminium electrode (effect surface area 75.56 cm ²)	Electro-modified BC with increased surface area and pore volume enhanced phosphate adsorption capacity from aqueous solution.	[196]
Cotton stalk	600	CO ₂ and NH ₃ gas used for modification. BC was heated up gradually to preset temperature (500-900 °C) and when the required temperature was reached, N ₂ gas replaced with CO ₂ /NH ₃ for modification	NH ₃ modification introduced N-functional groups and CO ₂ modification plays a significant role in pore formation. NH ₃ modification increased CO ₂ adsorption capacity of BC (99 mg/g)	[1]
Loblolly pine (<i>Pinus</i>)	600 for 1 h (10	The Mn-oxide modification was conduction	Mn-oxide modified BC enhanced sorption of	[197]

<i>taeda</i>) wood	°C per min)	by using $\text{MnCl}_2 \cdot 4\text{H}_2\text{O}$ for 2 h immersing. Final product was oven dried at 80 °C for overnight	As(V) and Pb (II). BC provides an effective way to produce low-cost C adsorbents for heavy metal remediation	
Pristine BC produced from <i>Eichhornia crassipes</i>	600	$\gamma\text{-Fe}_2\text{O}_3$ composite and chitosan were used for modification. Biomass dried and immersed in FeCl_3 solution and pyrolyzed. Later this product used for chitosan modification using acetic acid and NaOH solution	Modified BC was successfully synthesized and applied to remove Cr(VI) from aqueous solution. After modification, improved functional groups on BC surface increased its Cr(VI) sorption ability	[198]
Chicken manure	450	Amine modification by using anhydrous NH_3 gas for treating BC for 1 h at 450 °C	Amine-modified BC with higher surface area and amine functional groups increased Cu(II) adsorption capacity. Modification improved Cu-binding sites on the BC surface	[199]
Conocarpus green waste	600	Chemical modification with either Mg or Fe salts was done by a method of chemical co-precipitation. Treated BC was named as MgO-BC and FeO-BC	Modified BCs were assessed for removal of NO_3 from aqueous solution and MgO-BC showed better removal capacity due to high surface area and strong ionic complexation through chemisorption	[200]
Rice husk	450-500	Methanol modification was done by using NaOH as a pre-treatment agent. Chemical modification includes esterification and reaction between the carbonyl groups of BC and methanol	The adsorption capacity of BC for TC is enhanced after methanol modification. Modification improved O-containing group properties of BC for TC adsorption	[128]
Whitewood (spruce)	792 (fast pyrolysis)	Steam activation was done. Activated BC was impregnated with various additives KCl, KBr, KI, NH_4I , and NH_4Br .	Impregnated activated BC improved Hg removal efficiency significantly compared to control	[201]

1108 BC: Biochar

1109

1110

1111 Table 5: Activation and pyrolysis methods for modification of biochar (BC) characteristics

Agent	Biochar modification	Pyrolysis (° C)	Activation (° C)	reference
Physical				
Gases (CO ₂ , O ₂ , etc.)	Increases porosity and surface area	700	700 to 900	[132, 133]
Steam	Formation of O- functional groups	700	700 to 900	[134]
Chemical				
H ₃ PO ₄ , HNO ₃ , H ₂ SO ₄ NaOH, KOH	Loss of micropores due to deterioration, increase in O- functional groups	170	400 to 500	[202, 203]
	Increase in O- functional groups	700	700 to 900 with steam	[204-206]
KMnO ₄ , H ₂ O ₂ /HClO ₄	Increase in O- functional groups	400, 700-750	150-200 (purification)	[145, 146]
Impregnation				
Mg	Increase in O functional groups	350	NA	[190]
Fe	Fe ₂ O ₃ nanoparticles on surface	250 to 400	700 to 900	[23, 128]
Al	AlOOH/nanoparticles on surface	600	NA	[207]
Grafting				
Poly-styrene-N3	Initiator binding to C nanotubes to adhere 2 ^o organic compound	NA	170	[148]

1112

C: Carbon, N: Nitrogen, P: Phosphorus, K: Potassium, CH₄: Methane, NH₃: Ammonia, N₂O: Nitrous oxide, NO: Nitrogen dioxide, and CO₂: Carbon dioxide

Figure 1. Direct and indirect effect of char materials on greenhouse gas (GHG) emissions

1128

1129 NH_3 : ammonia volatilization, N_2O : nitrous oxide emission and NO_3^- : nitrate leaching

1130 Figure 2. Nitrogen dynamics and transformation in soil [adapted from [208]]

1131

1132 Figure 3: Carbon cycle and production of carbon dioxide (CO₂) throughout the earth
1133 involving various systems

1134

1135 Figure 4: Schematic diagram showing mechanisms for biochar induced mitigation of
 1136 ammonia volatilization, nitrous oxide emission and nitrate leaching

Figure 5: Overview of factors and mechanisms affecting the priming effect (PE) of native soil organic matter (SOM) by char/biochar addition in soil. Acceleration of SOM decomposition is referred to as positive PE and retardation of SOM decomposition is referred to as negative PE. Char intrinsic and external (soil, plant or environment) factors relating to PE have been listed. The likely biotic and abiotic processes for the positive or negative PE by direct or indirect mechanisms have been included. See the main text for the expanded explanation. The schematization of PE is adapted from [110]

Figure 6: Reaction scheme showing iron (Fe)-modified biochar reduces N_2O emission

Figure 7: Schematic diagram showing enhanced characteristics of modified biochar

1155

1156

1157

1158

1159

1160

1161

1162

1163

1164

1165

1166